The listing of claims will replace all prior versions, and listings, of claims in the application:

## **Listing of Claims:**

1. (Currently Amended) A heat treatment method comprising the steps of:

holding a treatment object in a processing chamber filled with a coolant for cooling the treatment object; chamber;

heating the treatment object by irradiating it through radiation with light from a lamp light source, source during a first period, while supply of a coolant is kept in the processing chamber; and

cooling the treatment object during a second period, while supply of the coolant is kept in the processing chamber,

wherein said lamp light source is turned on and [[the]] a radiation from said lamp light source is held for 0.1 to 20 seconds at a time, while supply of the coolant is kept, in the first period,

wherein a temperature drop rate by the supply of the coolant is 50 to 150° C per second in the second period, and

wherein one cycle including the first period and the second period is repeated several times.

2. (Withdrawn) A heat treatment method comprising the step of:

heating a treatment object by irradiating it through radiation from a lamp light source.

wherein the radiation from said lamp light source is pulsatively repeated several times such that the treatment object holds the temperature to its highest for 0.5 to 5 seconds.

3. (Currently Amended) A heat treatment method comprising the steps of: holding a treatment object in a processing chamber filled with a coolant for

cooling the treatment object; and chamber;

heating the treatment object by irradiating it through radiation with light from a lamp light source, source during a first period, while supply of a coolant is kept in the processing chamber; and

cooling the treatment object during a second period, while supply of the coolant is kept in the processing chamber,

wherein [[the]] a radiation from said lamp light source is held for 0.1 to 20 seconds at a [[time,]] time in the first period,

wherein the radiation from said lamp light source is repeated several times, while supply of the coolant is kept, times in the first period,

wherein a temperature drop rate by the supply of the coolant is 50 to 150° C per second in the second period, and

wherein one cycle including the first period and the second period is repeated several times.

4. (Withdrawn) A heat treatment method comprising the steps of: holding a treatment object in a processing chamber filled with a coolant; and heating the treatment object by irradiating it through radiation from a lamp light source,

wherein the radiation from said lamp light source is repeated several times such that the treatment object holds the temperature to its highest for 0.5 to 5 seconds.

5. (Currently Amended) A heat treatment method comprising the steps of: holding a treatment object in a processing chamber filled with a coolant for cooling the treatment object; and chamber;

heating the treatment object by irradiating it through radiation with light from a lamp light source, source during a first period, while supply of a coolant is kept in the

processing chamber; and

cooling the treatment object during a second period, while supply of the coolant is kept in the processing chamber,

wherein said lamp light source is turned on and [[the]] <u>a</u> radiation from said lamp light source is held for 0.1 to 20 seconds <u>at a time</u>, <u>while supply of the coolant is kept</u>, <u>in</u> the first period,

wherein said lamp light source is turned off while a treatment of increasing the amount of supply of the coolant as one cycle is repeated several times so that a temperature drop rate is 50 to 150° C per second in the second period, and

wherein one cycle including the first period and the second period is repeated several times.

6. (Withdrawn) A heat treatment method comprising the steps of: holding a treatment object in a processing chamber filled with a coolant; and heating the treatment object by irradiating it through radiation from a lamp light source.

wherein said lamp light source is turned on while an amount of supply of the coolant is reduced.

wherein said lamp light source is turned off while a treatment of increasing the amount of supply of the coolant as one cycle is repeated several times, after the treatment object holds the temperature to its highest for 0.5 to 5 seconds.

7. (Original) A heat treatment method according to claim 1, wherein said lamp light source is selected from the group consisting of a halogen lamp, a metal halide lamp, a xenon lamp, a high pressure mercury lamp, a high pressure sodium lamp and an excimer lamp.

8. (Withdrawn) A heat treatment method according to claim 2, wherein said lamp light source is selected from the group consisting of a halogen lamp, a metal

halide lamp, a xenon lamp, a high pressure mercury lamp, a high pressure sodium lamp

and an excimer lamp.

- 9. (Original) A heat treatment method according to claim 3, wherein said lamp light source is selected from the group consisting of a halogen lamp, a metal halide lamp, a xenon lamp, a high pressure mercury lamp, a high pressure sodium lamp and an excimer lamp.
- 10. (Withdrawn) A heat treatment method according to claim 4, wherein said lamp light source is selected from the group consisting of a halogen lamp, a metal halide lamp, a xenon lamp, a high pressure mercury lamp, a high pressure sodium lamp and an excimer lamp.
- 11. (Original) A heat treatment method according to claim 5, wherein said lamp light source is selected from the group consisting of a halogen lamp, a metal halide lamp, a xenon lamp, a high pressure mercury lamp, a high pressure sodium lamp and an excimer lamp.
- 12. (Withdrawn) A heat treatment method according to claim 6, wherein said lamp light source is selected from the group consisting of a halogen lamp, a metal halide lamp, a xenon lamp, a high pressure mercury lamp, a high pressure sodium lamp and an excimer lamp.

## 13. (Withdrawn) A heat treatment method comprising the step of:

heating a treatment object having a semiconductor film by irradiating it through radiation from a lamp light source,

wherein the radiation from said lamp light source lasts 0.1 to 20 seconds at a time,

wherein the radiation from said lamp light source is repeated several times.

## 14. (Withdrawn) A heat treatment method comprising the steps of:

holding a treatment object having a semiconductor film in a processing chamber filled with a coolant; and

heating the treatment object by irradiating it through radiation from a lamp light source.

wherein the radiation from said lamp light source is held for 0.1 to 20 seconds at a time,

wherein the radiation from said lamp light source is repeated several times.

## 15. (Withdrawn) A heat treatment method comprising the steps of:

holding a treatment object having a semiconductor film in a processing chamber filled with a coolant; and

heating the treatment object by irradiating it through radiation from a lamp light source,

wherein said lamp light source is turned on and the radiation from said lamp light source is held for 0.1 to 20 seconds at a time, while an amount of supply of the coolant is reduced,

wherein said lamp light source is turned off while a treatment of increasing the amount of supply of the coolant as one cycle is repeated several times.

16. (Withdrawn) A heat treatment method according to claim 13, wherein said lamp light source is selected from the group consisting of a halogen lamp, a metal

halide lamp, a xenon lamp, a high pressure mercury lamp, a high pressure sodium lamp

and an excimer lamp.

- 17. (Withdrawn) A heat treatment method according to claim 14, wherein said lamp light source is selected from the group consisting of a halogen lamp, a metal halide lamp, a xenon lamp, a high pressure mercury lamp, a high pressure sodium lamp and an excimer lamp.
- 18. (Withdrawn) A heat treatment method according to claim 15, wherein said lamp light source is selected from the group consisting of a halogen lamp, a metal halide lamp, a xenon lamp, a high pressure mercury lamp, a high pressure sodium lamp and an excimer lamp.
- 19. (Previously Presented) A heat treatment method according to claim 1, wherein the coolant is an inactive gas comprising at least one of nitrogen and helium.
- 20. (Previously Presented) A heat treatment method according to claim 3, wherein the coolant is an inactive gas comprising at least one of nitrogen and helium.
- 21. (Previously Presented) A heat treatment method according to claim 5, wherein the coolant is an inactive gas comprising at least one of nitrogen and helium.